



YADA TRADING COMPANY L.L.C.
شركة ياداد للتجارة ذ.م.م

Specifications of Bitumen Penetration 60/70

Bitumen60/70	Test method	Unit	Specification
Specific gravity@25°C	ASTM D70	Kg/cm3	1.01/1.06
Penetration@25°C	ASTM D5	mm/10	60/70
Softening point °C	ASTM D36	°C	49/56
Ductility @25°C	ASTM D113	Cm	100 min
Loss on heating (wt) %	ASTM D6	wt %	0.2 max
Drop in penetration after heating %	ASTM D5-D6	%	20 max
Flashpoint °C	ASTM D92	°C	232 min
Solubility in trichloroethylene	ASTM D2042	wt%	99 min
Spot test	A.A.S.H.O.T102		Negative